

HYLOMAR ADVANCED FORMULATION HV

High viscosity version of Hylomar Advanced Formulation

Description

Hylomar Advanced Formulation (HV) is ideally suited for use as a gasket dressing. It will enhance the sealing capability of all types of gasket and assist with alignment during assembly. The compound has excellent rheological properties, combined with resistance to most automotive fluids and many other chemicals. Being a non-setting and non-hardening compound it also has excellent resistance to joint vibration, shock and differential thermal expansion.

Physical Properties

Colour	Blue
Specific Gravity	1.18
Viscosity Spindle No 7 @ 2.5 rpm. 25°C.	1,100,000 cps
Solubility in Water	None
Flash Point	Over 392°C
Appearance	Non setting paste
Typical temperature range	-55°C to +250°C
Surface Finish Max	3.0 µm Ra
Area covered by 100 g	2.0 m ²
Shelf life	3 Years when stored in the original unopened containers between 5° to 25°

Instructions for use

Hylomar Advanced Formulation (HV) is a non-slump thixotropic gel and can be applied from a cartridge using hand pressure and a suitable applicator or by using automated dispensing equipment.

After applying to the joint surface, parts can be assembled immediately or may be left indefinitely before making the joint.

Typical Applications

Hylomar Advanced Formulation (HV) has been designed to seal close fitting flanges against most lubricants and automotive fluids. Although this material has many potential general engineering applications, it is currently being used for the sealing of components such as cylinder liners to engine block, cylinder head cam caps, electric motor end plate covers, fuel injector gland nuts.

Unlike Hylomar Universal Blue, Advanced Formulation will not have a film thickness between the flanges as it is a mobile product. It is designed to fill and seal all the surface imperfections in the flanges surfaces. Any resultant film thickness will depend entirely on the engineered texture of the flange mating surfaces.

Information given in this publication is based upon technical data gained in our own and other Laboratories and is believed to be true. However the material is used in conditions beyond our control thus we can assume no liability for results obtained or damages incurred through the application of the data present herein.

Hylomar Ltd, Cale Lane, Wigan WN2 1JT UK Tel: +44 (0) 1942 617000 Fax: +44 (0) 1942 617001	Revision date	17.05.2010	Page 1 of 2
	Product name	Hylomar Advanced Formulation HV Version 5	

Hylomar Advanced Formula (HV) can be removed from dismantled components by rubbing with a cloth soaked with Acetone. No scraping is necessary.

Handling and Safety Properties

Hylomar Advanced Formulation (HV) is classed as a non-hazardous product.
Safety phrases S37.

Packaging

Hylomar Advanced Formulation (HV) is available in 350g cartridges and 20Kg pails. For further details please contact our sales department.

Information given in this publication is based upon technical data gained in our own and other Laboratories and is believed to be true. However the material is used in conditions beyond our control thus we can assume no liability for results obtained or damages incurred through the application of the data present herein.

Hylomar Ltd, Cale Lane, Wigan WN2 1JT UK Tel: +44 (0) 1942 617000 Fax: +44 (0) 1942 617001	Revision date	17.05.2010	Page 2 of 2
	Product name	Hylomar Advanced Formulation HV Version 5	